## DS FOAM 3.0
Fixing, mounting and fastening

**3.0 foam, medium adhesion**
Thick double sided foam tape suitable for mounting dispensers, numbers plates and other general purpose applications. Excellent adhesion and holding power.

| BACKING | ADHESIVE | COLOUR | TOTAL THICKNESS | ADHESION | TENSILE STRENGTH | ELONGATION TO BREAK | TEMPERATURE RESISTANCE |
|---|---|---|---|---|---|---|---|
| Foam | Acrylic adhesive | White (white paper liner) | 3.000 mm | > 19.6 N/25mm | \ | \ | 60°C |

## TB7772 TOUGH BOND WHITE
Fixing, mounting and fastening

**Foam like solvent acrylic adhesive**
Film of viscoelastic adhesive tape. The adhesive bonds to a wide range of material including metal and glass. Most substrates are best prepared by cleaning with 50:50 mixture of isopropyl alcohol ( IPA) and water prior to applying.

| BACKING | ADHESIVE | COLOUR | TOTAL THICKNESS | ADHESION | TENSILE STRENGTH | ELONGATION TO BREAK | TEMPERATURE RESISTANCE |
|---|---|---|---|---|---|---|---|
| Foam | Solvent acrylic | White (MOPP red liner) | 1.100 mm | 49 N/25 mm (90° peel adhesion) | 50 N/25mm | \ | 150°C |

## TB7774 TOUGH BOND TRANSPARENT
Fixing, mounting and fastening

**Foam like solvent acrylic adhesive**
Film of viscoelastic adhesive tape. The adhesive bonds to a wide range of material including metal and glass. Most substrates are best prepared by cleaning with 50:50 mixture of isopropyl alcohol ( IPA) and water prior to applying.

| BACKING | ADHESIVE | COLOUR | TOTAL THICKNESS | ADHESION | TENSILE STRENGTH | ELONGATION TO BREAK | TEMPERATURE RESISTANCE |
|---|---|---|---|---|---|---|---|
| Foam | Solvent acrylic | Transparent (MOPP red liner) | 1.000 mm | 49 N/25 mm (90° peel adhesion) | \ | \ | 80°C |

## TB7776 TOUGH BOND GREY
Fixing, mounting and fastening

**Foam like solvent acrylic adhesive**
Film of viscoelastic adhesive tape. The adhesive bonds to a wide range of material including metal and glass. Most substrates are best prepared by cleaning with 50:50 mixture of isopropyl alcohol ( IPA) and water prior to applying.

| BACKING | ADHESIVE | COLOUR | TOTAL THICKNESS | ADHESION | TENSILE STRENGTH | ELONGATION TO BREAK | TEMPERATURE RESISTANCE |
|---|---|---|---|---|---|---|---|
| Foam | Solvent acrylic | Grey (MOPP red liner) | 1.100 mm | 69 N/25 mm (90° peel adhesion) | 45 N/25mm | \ | 90°C |